



## Super FG

### Superior Food-Machinery Grease, Grade #2

Kosher Certified and Rated H1 for Incidental Contact with Food

#### Description

**Super FG** is distinguished by its exceptional mechanical stability, high dropping point and performance under water wash out. It is a state of the art, high performance grease which outperforms other premium greases such as Lithium Complex, Aluminum Complex and Polyurea.

#### Applications

Super FG is a Food Grade Grease for use above and below the line of production. It is designed for use in all food processing areas including mixing, baking, cooking, frying, stirring, packaging, cleansing, bottling and canning.

#### Features and Benefits

- Thermal and Mechanical Stability, particularly in the presence of heat and water
- Very Wide Temperature Range (-40 F to 608 F)
- Resists Heavy Loads
- Excellent EP and Anti-Wear Properties
- Resistance to Water Wash-Out
- Resists many Acid and Alkaline Solutions
- Does Not Dry

Extreme Industrial Lubricants, Inc.  
26873 Sierra Hwy, Suite 133 || Santa Clarita CA, 91321 USA  
Tel: 661-298-8510  
*Web Site: [www.extremelubricants.com](http://www.extremelubricants.com)*

The product information and specifications contained here in have been compiled for the convenience of the user. It is intended to be used by people with technical skills. Extreme Industrial Lubricants disclaims any warranty, expressed or implied, of merchantability. Whenever the information herein is to be used for a critical application, it should be verified independently. This information is not intended as a license to operate under, or a recommendation to infringe any patent.

**EXTREME INDUSTRIAL LUBRICANTS, INC.**

Santa Clarita CA, 91321

**Superior Food Grade Grease, Grade #2**

<b>Tech Data for Super FG GREASE, Grade #2, Base Oil Viscosity ISO 320</b>				
<b>Property</b>	<b>Test Method</b>	<b>Units</b>	<b>Super FG #2</b>	
Color	Visual		Tan	
Worked Penetration, 60 Strokes @ 25°C	ASTM D-217	mm/10	280	
Mechanical Stability	ASTM D-217 % change	10,000 Strokes	1.0	
Shell Roll Stability	ASTM D-1831	% change from P60	2.1	
Timken OK Load	ASTM D-2509	lbs. / kg.	80/36	
4-Ball EP Weld Load LWI	ASTM D-2596	Kgf.	500 kg. 62 kg	
4 Ball Wear, Scar Dia. (40kg., Load, 1200 RPM, 75°C, 1-hr.)	ASTM D-2266	Average Wear Scar in mm	0.45 mm	
Dropping Point	ASTM D 2265	°C (°F)	318 C (608 F)	
Rust Test Copper Corrosion Salt Fog Spray	ASTM D-1743 ASTM D-130 ASTM B-117	Rating Classification Hours to Failure	Pass 1B >300	
Water Washout	ASTM D-1264, @ 80 °C	% Loss	0.5%	
Oxidation Bearing Life Rotary Bomb Oxidation	ASTM D-3527 ASTM D-942	Hrs. PSI drop, 1000 hrs.	180 6.0	

*Subject to Usual Manufacturing Tolerances*

**Extreme Industrial Lubricants, Inc.**

26873 Sierra Hwy, Suite 133 || Santa Clarita CA, 91321 USA

Tel: 661-298-8510

Web Site: [www.extremelubricants.com](http://www.extremelubricants.com)

The product information and specifications contained here in have been compiled for the convenience of the user. It is intended to be used by people with technical skills. Extreme Industrial Lubricants disclaims any warranty, expressed or implied, of merchantability. Whenever the information herein is to be used for a critical application, it should be verified independently. This information is not intended as a license to operate under, or a recommendation to infringe any patent.